

HYDRO POLYMER (CLEAR & PIGMENTED)

Moisture-Mitigating Flexible High-Build Coating

Description: Two-component, high-solids, moisture-mitigating industrial floor coating for permanent protection with a smooth or anti-skid seamless surface. Typically used as a primer coat where moisture vapor transmission readings exceed tolerance and where odor-sensitive application is required.

Areas of Usage: When used in combination with the appropriate topcoat, for use in both interior or exterior installations including warehouses, manufacturing facilities (food preparation, food processing, and chemical processing plants), parking lots, chemical storage areas, laboratories, airplane hangars, washrooms, showers, garages, basements, walls, patios, walkways and handicap ramps.

Features / Advantages:	Pigmented or clear	Quick dry properties
	Moisture-mitigating system	Outstanding flow and leveling
	Water-proofing system	High strength and flexibility
	Low VOC	Superior adhesion
	Impermeable	Chemical and stain resistant
	Low odor	Molecularly bonding

Surface Preparation: Allow new concrete to cure for at least 30 days prior to preparation and coating. Test for moisture and remove dust, laitance, grease, curing compounds, preparation bond-inhibiting impregnations, waxes and other contaminants. Prepare concrete via mechanical abrasion (grinding, bead-blasting, diamond grinding) or chemical treatment (acid washing followed by alkali neutralization).

Technical Data: Note: Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions

Packaging: Part A and Part B Activator 5 gallon kit (54.0 lbs); 4 gallon Part A & 1 gallon Part B. Approximate weight; may vary depending upon pigment and fill level

Mixing Ratio: Four parts clear or colored resin (Part A) to one part catalyst (Part B), i.e., 4:1 ratio by volume; the mixture may be diluted with solvent. Pigments may be added for custom color applications

Application: Polyester brush and 9", 14" or 18" rollers with microfiber nap

Average Dry Time at 77°F (25°C): Dry times vary depending upon weather conditions. **Cure to Tack-Free:** 4 - 6 hours; **Cure to Tack Form:** 1 - 2 hours; **Waiting Time Between Coats:** 12 - 24 hours (sand if >36 hours); **Full Cure:** 7 days. *Note: A 100% Solids Polymer may be applied over the Hydro Polymer within 2 - 4 hours; however, this only applies to the moisture-tolerant 100% Solids Polymer and does not apply to a Poly Hybrid or Poly 3000*

Resistance To: Moisture, stains, chemicals and abrasion (e.g., water, mold, mildew, salt, grease, oil and other petroleums, animal fat, feces, urine, bleach, solvents, chemical fumes, non-oxidizing acids, alkalis, alcohols)

HYDRO POLYMER (CLEAR & PIGMENTED)

Moisture-Mitigating Flexible High-Build Coating

Technical Data (Con't): *Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions*

Reducing: May be reduced with xylene or citrus solvent (or combinations thereof); consult local air district rules or regulations

Finish: Low gloss

Colors: Clear, White, Tumbleweed, Silver Grey, Mohave, Pebble Beach and mixtures thereof; custom colors available upon request

% Solids (Vol): Average of 40% (depending on pigment)

% Solids (Wt): Average of 50% (depending on pigment)

Pigment Type: Chemical resistant

Vehicle Type: Acrylic modified epoxy

Viscosity: 60 sec on Zahn 2

Physical Properties: VOC Actual: 189 g/l; VOC Regulatory: 141 g/l mixed; Weight of Volatiles: 39.8%; Weight of Exempt: 38.9%; Volume of Exempt: 48.5%; Density: 1,258 g/l

Thickness: Recommended installation of 10 mils wet per coat

Flexural Strength: Not available

Compression Strength: Not available

Pot Life: Pot life applies to material poured immediately onto the substrate following preparation. Pot Life = 1 hour for 1 - 2 gallons at 77°F (25°C) and 50% relative humidity (RH). If ambient temperature is greater than 77°F and / or RH greater than 50%, pot life is dramatically shortened

Shelf Life: 12 months at 77°F (25°C) when Parts A and B are not combined

HYDRO POLYMER (CLEAR & PIGMENTED)

Moisture-Mitigating Flexible High-Build Coating

Mixing: Pigmented and clear Hydro Polymers are two component systems: Part A and Part B (the activator). Mix Part A and Part B in a ratio of 4:1 as follows (do not mix until ready to use): thoroughly mix the pigmented Part A component separately, ensuring a uniform color. Then, add 4 parts Part A and 1 part Part B in a bucket and mix immediately. Always mix at a slow mixing speed to avoid introducing air into the mixture. After thoroughly mixing Parts A and B, a reducer may be added; if so, re-mix thoroughly.

Application Procedure: The pigmented and clear Hydro Polymer may be used in a variety of coating systems as a moisture-mitigating primer coat.

Handling and Storage: Store in a cool, dry, well ventilated area. Keep containers tightly closed.

• KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • INDUSTRIAL GRADE • HANDLING AND INSTALLATION MUST BE PERFORMED BY ECO-CORFLEX-CERTIFIED APPLICATORS ONLY •

All information provided by Eco-CorFlex concerning its products, including but not limited to, any recommendations and advice relating to the application and use, is given in good faith based on Eco-CorFlex's current experience and knowledge of its products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Eco-CorFlex's control are such that Eco-CorFlex assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of Eco-CorFlex product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application. Eco-CorFlex reserves the right to change the properties of its products without notice.

Prior to each use of any Eco-CorFlex product, the user must read and follow the warnings and instructions on the products most current Technical Data Sheet, product label and Safety Data Sheet which are available online at www.ecocorflex.com or by calling Eco-CorFlex at 866-406-2628. Eco-CorFlex warrants this product to be free of manufacturing defects and warrants this product to meet the technical properties on the current Technical Data Sheet if used as directed within the shelf life. The user must determine suitability of each product for its intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of the product *exclusive of labor or cost of labor*.

ECO-CORFLEX MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED.